



28, avenue Franklin Roosevelt – 69120 VAULX-EN-VELIN  
Tél : +33 (04).78.49.01.61 – Fax : +33 (04).78.49.12.59 - Email : [sofiplast@sofiplast.fr](mailto:sofiplast@sofiplast.fr)

## **Product Data Sheet AS 235**

### **General information :**

- *Excellent NON-STICK properties*
- *Low friction coefficient*
- *Good resistance to ABRASION*
- *Working temperature of - 10°C to + 260°C*
- *Good resistance to chemical agents*
- *Conforms to BGA, BSI and FDA standards relating to coatings used in the FOOD sector*
- *Curing temperature between 400°C and 425°C*
- *Dry film thickness recommended : 35 to 40 approximately*

### **Applications :**

- ***AS 235** coating is suitable for use on COOKING equipment (moulds, plates, mesh, grilles ...), STORAGE equipment (tanks, hoppers, reservoirs) and CONVEYORS for various foodstuffs ...*
- ***AS 235** coating is regularly used on utensils used in the food industry to facilitate their removal from moulds (cutting cylinders, plates, moulds, patterns) and for cleaning (oil, grease, pastes...)*
- ***AS 235** coating is regularly used on domestic utensils used for cooking (pots and pans, casserole dishes, spatulas ...)*

***AS 235** coating enables you to solve most of the problems you may experience with adhesion, sticking and associated malfunctions, and reduces maintenance and cleaning time, increases your production rates and improves the life of your equipment ...*

The information contained in product sheet No. 235\_2011 is for guidance purposes only. It may be subject to variation depending on the supply, nature and shape of the parts.