



28, avenue Franklin Roosevelt – 69120 VAULX-EN-VELIN
Tél : +33 (04).78.49.01.61 – Fax : +33 (04).78.49.12.59 - Email : sofiplast@sofiplast.fr

Product Data Sheet AS 26

General properties :

- *Excellent non-stick properties*
- *Very good abrasion resistance*
- *Low coefficient of friction*
- *Excellent dielectric resistance*
- *Excellent chemical, weather and ultraviolet rays resistance*
- *Operating temperature from - 240°C (465°F) to + 260°C (500°F)*
- *Complies with BGA and FDA specifications concerning coating for food use*
- *Cure temperature between 330°C (626°F) and 400°C (752°F)*
- *Dry film thickness : from 40 to 100 microns*

Applications :

- *Our coating **AS 26** both oleophobic and hydrophobic therefore hard to wet, is used in many manufacture process for sticking products as liquids and pasta, rubbers, plastics...*
- *Our coating **AS 26** is used on TRANSPORT, MOULDING and FIRING equipment of those same products, particularly foodstuffs*
- *Our coating **AS 26** is used on equipment, which need both non-stick properties and a corrosive **AS 26** is used on various materials, which need both a chemical and a dielectric resistance (sounding machine, pliers or handle...)*
- *Our coating **AS 26** is used on cylinders and drier basket for paper and textile industries.*

*Our coating **AS 26** will enable you to resolve simultaneously most of your sticking, clogging and corrosion protection problems, to reduce your maintenance and cleaning time, to improve your equipment lifetime...*

The pieces of information on this sheet AS 26_2011 are given as a rough guide. They are subjected to variations according to the supply, nature and shape of the part.