



28, avenue Franklin Roosevelt – 69120 VAULX-EN-VELIN
Tél : +33 (04).78.49.01.61 – Fax : +33 (04).78.49.12.59 - Email : sofiplast@sofiplast.fr

Product Data Sheet AS 37

General information :

- *Excellent NON-STICK properties*
- *Very good resistance to ABRASION*
- *Working temperature of - 40°C to + 200°C*
- *Excellent ANTI-STATIC properties*
- *Good resistance to various chemical agents*
- *Conforms to BGA, BSI and FDA standards relating to coatings used in the FOOD sector*
- *Curing temperature between 380°C and 400°C*
- *Dry film thickness recommended : 40 microns minimum*

Applications :

- **AS 37** coating is suitable for **MOULDING** equipment (moulds, cores, dies), **STORAGE** (tanks, hoppers, reservoirs) and **CONVEYORS** (waste chutes, feeding screws, conveyor rollers and plates), in materials as diverse as plastic adhesive, powders, food packaging ...
- **AS 37** coating is used on booths or painting chains to facilitate their cleaning (grates, carrier conveyors, hoods),
- **AS 37** coating is used on cylinders or heated rollers for the plastics industry,
- **AS 37** coating is used on cutting assemblies (blades, dies, rotation cutting blades) dough for the biscuit and bakery industry.

AS 37 coating enables you to solve most of the problems you may experience with adhesion, sticking and associated operating malfunctions, and eliminates electro-static charges, reduces maintenance and cleaning time, increases your production rates and improves the life of your equipment ...

The information contained in product sheet AS37_2011 dated September 1998 is given for guidance purposes only. It may be subject to variation depending on the supply, nature and shape of the parts.